



Polycarbonate

Colour: Clear

Density: 1.20g/cm³

Material Data Sheet

Mechanical Properties	Parameter	Value	Unit	DIN/EN/ISO
Tensile strength at yield	50mm/min	60	MPa	527
Tensile strength at break	50mm/min	70	MPa	527
Tensile strain at yield	50mm/min	6	%	527
Tensile strain at break	50mm/min	120	%	527
Flexural strength at yield	2mm/min	90	MPa	178
Modulus of elasticity (flexural test)	2mm/min	2300	MPa	178
Izod impact strength 23 °C	Notched	65	kJ/m ²	180/4A
Izod impact strength -30 °C	Notched	10	kJ/m ²	180/4A
Impact strength (Charpy)	Notched	35	kJ/m ²	179/1C
Hardness	H358/30 95	95	Mpa	2039/1

Thermal Properties	Parameter	Value	Unit	DIN/EN/ISO
Vicat softening temperature	B/120	145	°C	306
HDT/Ae, 1.8 MPa edgew.	120*1*04/sp=100	127	°C	75
Thermal conductivity	-	0.2	W/m.°C	8302
Coeff. Of lin. Therm. Exp. Extr.	23-80 °C	7.00 E-05	1/°C	11359-2
Ball pressure test	125 +2 °C	Passes	-	60695-10-2
Relative thermal index	Electrical Prop.	130	°C	746B
Relative thermal index	Mech. Prop. With impact	125	°C	746B
Relative thermal index	Mech. Prop. w/o impact	125	°C	746B

Electrical properties	Parameter	Value	Unit	DIN/IEC
Volume resistivity	-	10E15	Ohm.cm	60093
Relative permittivity	50/60Hz	2.7	-	60250
Relative permittivity	1Mhz	2.7	-	60250
Dissipation factor	50/60Hz	0.001	-	60250
Dissipation factor	1Mhz	0.01	-	60250

Other properties	Parameter	Value	Unit	DIN/EN/ISO/IEC
Water absorption	50%RH / 23°C	0.15	%	62
Water absorption	Saturation/23°C	0.35	%	62
Light transmission	3mm	-	119	D495

Direct Plastics Ltd. Rother Valley Way, Holbrook, Sheffield, S20 3RW

The following information corresponds with our current knowledge and indicates our products and possible applications. We cannot give a legally binding guarantee of certain properties or the suitability for a specific application. Existing commercial patents must be observed. A definitive quality guarantee is given in our general

conditions of sales. Unless otherwise stated, these values represent averages taken from injection moulding samples.

We reserve the right of technical alterations.